

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
16 October 2003 (16.10.2003)

PCT

(10) International Publication Number
WO 03/085197 A1

(51) International Patent Classification⁷: **D21F 7/08**, 7/10

(21) International Application Number: PCT/US03/07534

(22) International Filing Date: 13 March 2003 (13.03.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/114,286 2 April 2002 (02.04.2002) US

(71) Applicant: **ALBANY INTERNATIONAL CORP.**
[US/US]; 1373 Broadway, Albany, NY 12204 (US).

(72) Inventor: **YOOK, Steven, S.**; 11 Castle Road, South
Glens Falls, NY 12803 (US).

(74) Agent: **SANTUCCI, Ronald, R.**; Frommer Laurence &
Haug LLP, 745 Fifth Avenue, New York, NY 10151 (US).


(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:
— with international search report

[Continued on next page]

(54) Title: LAMINATED MULTIAXIAL PRESS FABRIC



(57) Abstract: An on-machine-seamable laminated multi-axial press fabric has a first base fabric and a second base fabric laminated to one another by needled staple fiber batt material. The first base fabric (22) is a multi-axial fabric produced by spirally winding a fabric strip (16), flattening the endless loop produced by the spiral winding, and removing crosswise yarns (28) at the ends of the flattened endless loop to form seaming loops (56). The second base fabric (60) is an on-machine-seamable base fabric, which may also be multi-axial. The press fabric is joined into endless form by interdigitating the seaming loops (56, 66) at the two ends of both base fabrics (22, 60) with one another to form a single passage through which a pintle (68) is passed to join the press fabric into endless form. Alternatively, the seaming loops (56, 66) at the two ends of each base fabric are interdigitated with one another to form two passages through which two pintles (52, 68) are passed to join the press fabric into endless form, each passage being on the opposite side of the other relative to its respective base fabric (22, 60).

WO 03/085197 A1



— *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

LAMINATED MULTIAXIAL PRESS FABRIC

Background of the Invention5 Field of the Invention

The present invention relates to the papermaking arts. More specifically, the present invention relates to press fabrics for the press section of a paper machine.

Description of the Prior Art

10 During the papermaking process, a cellulosic fibrous web is formed by depositing a fibrous slurry, that is, an aqueous dispersion of cellulose fibers, onto a moving forming fabric in the forming section of a paper machine. A large amount of water is drained from the slurry through the forming fabric, leaving the cellulosic fibrous web on the surface of the forming fabric.

15 The newly formed cellulosic fibrous web proceeds from the forming section to a press section, which includes a series of press nips. The cellulosic fibrous web passes through the press nips supported by a press fabric, or, as is often the case, between two such press fabrics. In the press nips, the cellulosic fibrous web is subjected to compressive forces which squeeze water therefrom, and which adhere the cellulosic fibers in the web to one another to turn the cellulosic fibrous web into
20 a paper sheet. The water is accepted by the press fabric or fabrics and, ideally, does not return to the paper sheet.

The paper sheet finally proceeds to a dryer section, which includes at least one series of rotatable dryer drums or cylinders, which are internally heated by steam. The newly formed paper sheet is directed in a serpentine path sequentially
25 around each in the series of drums by a dryer fabric, which holds the paper sheet closely against the surfaces of the drums. The heated drums reduce the water content of the paper sheet to a desirable level through evaporation.

It should be appreciated that the forming, press and dryer fabrics all take the form of endless loops on the paper machine and function in the manner of
30 conveyors. It should further be appreciated that paper manufacture is a continuous process which proceeds at considerable speeds. That is to say, the fibrous slurry is

continuously deposited onto the forming fabric in the forming section, while a newly manufactured paper sheet is continuously wound onto rolls after it exits from the dryer section.

5 The present invention relates specifically to the press fabrics used in the press section. Press fabrics play a critical role during the paper manufacturing process. One of their functions, as implied above, is to support and to carry the paper product being manufactured through the press nips.

10 Press fabrics also participate in the finishing of the surface of the paper sheet. That is, press fabrics are designed to have smooth surfaces and uniformly resilient structures, so that, in the course of passing through the press nips, a smooth, mark-free surface is imparted to the paper.

15 Perhaps most importantly, the press fabrics accept the large quantities of water extracted from the wet paper in the press nip. In order to fill this function, there literally must be space, commonly referred to as void volume, within the press fabric for the water to go, and the fabric must have adequate permeability to water for its entire useful life. Finally, press fabrics must be able to prevent the water accepted from the wet paper from returning to and rewetting the paper upon exit from the press nip.

20 Contemporary press fabrics are produced in a wide variety of styles designed to meet the requirements of the paper machines on which they are installed for the paper grades being manufactured. Generally, they comprise a woven base fabric into which has been needled a batt of fine, non-woven fibrous material. The base fabrics may be woven from monofilament, plied monofilament, multifilament or plied multifilament yarns, and may be single-layered, multi-layered or laminated. The
25 yarns are typically extruded from any one of several synthetic polymeric resins, such as polyamide and polyester resins, used for this purpose by those of ordinary skill in the paper machine clothing arts.

30 The woven base fabrics themselves take many different forms. For example, they may be woven endless, or flat woven and subsequently rendered into endless form with a woven seam. Alternatively, they may be produced by a process commonly known as modified endless weaving, wherein the widthwise edges of the base fabric are provided with seaming loops using the machine-direction (MD) yarns

thereof. In this process, the MD yarns weave continuously back and forth between the widthwise edges of the fabric, at each edge turning back and forming a seaming loop. A base fabric produced in this fashion is placed into endless form during installation on a paper machine, and for this reason is referred to as an on- machine-
5 seamable fabric. To place such a fabric into endless form, the two widthwise edges are brought together, the seaming loops at the two edges are interdigitated with one another, and a seaming pin or pintle is directed through the passage formed by the interdigitated seaming loops.

Further, the woven base fabrics may be laminated by placing one base fabric
10 within the endless loop formed by another, and by needling a staple fiber batt through both base fabrics to join them to one another. One or both woven base fabrics may be of the on- machine-seamable type.

In any event, the woven base fabrics are in the form of endless loops, or are seamable into such forms, having a specific length, measured longitudinally
15 therearound, and a specific width, measured transversely thereacross. Because paper machine configurations vary widely, paper machine clothing manufacturers are required to produce press fabrics, and other paper machine clothing, to the dimensions required to fit particular positions in the paper machines of their customers. Needless to say, this requirement makes it difficult to streamline the
20 manufacturing process, as each press fabric must typically be made to order.

In response to this need to produce press fabrics in a variety of lengths and widths more quickly and efficiently, press fabrics have been produced in recent years using a spiral technique disclosed in commonly assigned U.S. Patent No. 5,360,656 to Rexfelt et al., the teachings of which are incorporated herein by
25 reference.

U.S. Patent No. 5,360,656 shows a press fabric comprising a base fabric having one or more layers of staple fiber material needled thereinto. The base fabric comprises at least one layer composed of a spirally wound strip of woven fabric having a width which is smaller than the width of the base fabric. The base fabric is
30 endless in the longitudinal, or machine, direction. Lengthwise threads of the spirally wound strip make an angle with the longitudinal direction of the press fabric. The

strip of woven fabric may be flat-woven on a loom which is narrower than those typically used in the production of paper machine clothing.

The base fabric comprises a plurality of spirally wound and joined turns of the relatively narrow woven fabric strip. The fabric strip is woven from lengthwise (warp) and crosswise (filling) yarns. Adjacent turns of the spirally wound fabric strip may be abutted against one another, and the helically continuous seam so produced may be closed by sewing, stitching, melting, welding (e.g. ultrasonic) or gluing. Alternatively, adjacent longitudinal edge portions of adjoining spiral turns may be arranged overlappingly, so long as the edges have a reduced thickness, so as not to give rise to an increased thickness in the area of the overlap. Further, the spacing between lengthwise yarns may be increased at the edges of the strip, so that, when adjoining spiral turns are arranged overlappingly, there may be an unchanged spacing between lengthwise threads in the area of the overlap.

In any case, a woven base fabric, taking the form of an endless loop and having an inner surface, a longitudinal (machine) direction and a transverse (cross-machine) direction, is the result. The lateral edges of the woven base fabric are then trimmed to render them parallel to its longitudinal (machine) direction. The angle between the machine direction of the woven base fabric and the helically continuous seam may be relatively small, that is, typically less than 10° . By the same token, the lengthwise (warp) yarns of the woven fabric strip make the same relatively small angle with the longitudinal (machine) direction of the woven base fabric. Similarly, the crosswise (filling) yarns of the woven fabric strip, being perpendicular to the lengthwise (warp) yarns, make the same relatively small angle with the transverse (cross-machine) direction of the woven base fabric. In short, neither the lengthwise (warp) nor the crosswise (filling) yarns of the woven fabric strip align with the longitudinal (machine) or transverse (cross-machine) directions of the woven base fabric.

In the method shown in U.S. Patent No. 5,360,656, the woven fabric strip is wound around two parallel rolls to assemble the woven base fabric. It will be recognized that endless base fabrics in a variety of lengths and widths may be provided by spirally winding a relatively narrow piece of woven fabric strip around the two parallel rolls, the length of a particular endless base fabric being determined

by the length of each spiral turn of the woven fabric strip, and the width being determined by the number of spiral turns of the woven fabric strip. The prior necessity of weaving complete base fabrics of specified lengths and widths to order may thereby be avoided. Instead, a loom as narrow as 20 inches (0.5 meters) could
5 be used to produce a woven fabric strip, but, for reasons of practicality, a conventional textile loom having a width of from 40 to 60 inches (1.0 to 1.5 meters) may be preferred.

U.S. Patent No. 5,360,656 also shows a press fabric comprising a base fabric having two layers, each composed of a spirally wound strip of woven fabric. Both
10 layers take the form of an endless loop, one being inside the endless loop formed by the other. Preferably, the spirally wound strip of woven fabric in one layer spirals in a direction opposite to that of the strip of woven fabric in the other layer. That is to say, more specifically, the spirally wound strip in one layer defines a right-handed spiral, while that in the other layer defines a left-handed spiral. In such a two-layer,
15 laminated base fabric, the lengthwise (warp) yarns of the woven fabric strip in each of the two layers make relatively small angles with the longitudinal (machine) direction of the woven base fabric, and the lengthwise (warp) yarns of the woven fabric strip in one layer make an angle with the lengthwise (warp) yarns of the woven fabric strip in the other layer. Similarly, the crosswise (filling) yarns of the
20 woven fabric strip in each of the two layers make relatively small angles with the transverse (cross-machine) direction of the woven base fabric, and the crosswise (filling) yarns of the woven fabric strip in one layer make an angle with the crosswise (filling) yarns of the woven fabric strip in the other layer. In short, neither the lengthwise (warp) nor the crosswise (filling) yarns of the woven fabric strip in
25 either layer align with the longitudinal (machine) or transverse (cross-machine) directions of the base fabric. Further, neither the lengthwise (warp) nor the crosswise (filling) yarns of the woven fabric strip in either layer align with those of the other.

As a consequence, the base fabrics shown in U.S. Patent No. 5,360,656 have no defined machine- or cross-machine-direction yarns. Instead, the yarn systems lie
30 in directions at oblique angles to the machine and cross-machine directions. A press fabric having such a base fabric may be referred to as a multiaxial press fabric. Whereas the standard press fabrics of the prior art have three axes: one in the

machine direction (MD), one in the cross-machine direction (CD), and one in the z-direction, which is through the thickness of the fabric, a multiaxial press fabric has not only these three axes, but also has at least two more axes defined by the directions of the yarn systems in its spirally wound layer or layers. Moreover, there are multiple flow paths in the z-direction of a multiaxial press fabric. As a consequence, a multiaxial press fabric has at least five axes. Because of its multiaxial structure, a multiaxial press fabric having more than one layer exhibits superior resistance to nesting and/or to collapse in response to compression in a press nip during the papermaking process as compared to one having base fabric layers whose yarn systems are parallel to one another.

Until recently, multiaxial press fabrics of the foregoing type had been produced only in endless form. As such, their use had been limited to press sections having cantilevered press rolls and other components, which permit an endless press fabric to be installed from the side of the press section. However, their relative ease of manufacture and superior resistance to compaction contributed to an increased interest and a growing need for a multiaxial press fabric which could be seamed into endless form during installation on a press section, thereby making such press fabric available for use on paper machines lacking cantilevered components. On-machine-seamable multiaxial press fabrics, developed to meet this need, are shown in commonly assigned U.S. Patents Nos. 5,916,421; 5,939,176; and 6,117,274 to Yook, the teachings of which are incorporated herein by reference.

U.S. Patent No. 5,916,421 shows an on-machine-seamable multiaxial press fabric for the press section of a paper machine made from a base fabric layer assembled by spirally winding a fabric strip in a plurality of contiguous turns, each of which abuts against and is attached to those adjacent thereto. The resulting endless base fabric layer is flattened to produce first and second plies joined to one another at folds at their widthwise edges. Crosswise yarns are removed from each turn of the fabric strip at folds at the widthwise edges to produce unbound sections of lengthwise yarns. A seaming element, having seaming loops along one of its widthwise edges, is disposed between the first and second fabric plies at each of the folds at the two widthwise edges of the flattened base fabric layer. The seaming loops extend outwardly between the unbound sections of the lengthwise yarns from

between the first and second fabric plies. The first and second fabric plies are laminated to one another by needling staple fiber batt material therethrough. The press fabric is joined into endless form during installation on a paper machine by directing a pintle through the passage formed by the interdigitation of the seaming loops at the two widthwise edges.

U.S. Patent No. 5,939,176 also shows an on-machine-seamable multiaxial press fabric. Again, the press fabric is made from a base fabric layer assembled by spirally winding a fabric strip in a plurality of contiguous turns, each of which abuts against and is attached to those adjacent thereto. The resulting endless fabric layer is flattened to produce a first and second fabric plies joined to one another at folds at their widthwise edges. Crosswise yarns are removed from each turn of the fabric strip at the folds at the widthwise edges to produce seaming loops. The first and second plies are laminated to one another by needling staple fiber batt material therethrough. The press fabric is joined into endless form during installation on a paper machine by directing a pintle through the passage formed by the interdigitation of the seaming loops at the two widthwise edges.

Finally, in U.S. Patent No. 6,117,274, another on-machine-seamable multiaxial press fabric is shown. Again, the press fabric is made from a base fabric layer assembled by spirally winding a fabric strip in a plurality of contiguous turns, each of which abuts against and is attached to those adjacent thereto. The resulting endless fabric layer is flattened to produce a first and second fabric plies joined to one another at folds at their widthwise edges. Crosswise yarns are removed from each turn of the fabric strip at the folds at the widthwise edges to produce unbound sections of lengthwise yarns. Subsequently, an on-machine-seamable base fabric, having seaming loops along its widthwise edges, is disposed between the first and second fabric plies of the flattened base fabric layer. The seaming loops extend outwardly between the unbound sections of the lengthwise yarns from between the first and second fabric plies. The first fabric ply, the on-machine-seamable base fabric and the second fabric ply are laminated to one another by needling staple fiber batt material therethrough. The press fabric is joined into endless form during installation on a paper machine by directing a pintle through the passage formed by the interdigitation of the seaming loops at the two widthwise edges.

The present invention is an alternative to those disclosed in these three patents in the form of a laminated multiaxial press fabric having more than one on-machine-seamable layer.

5

SUMMARY OF THE INVENTION

Accordingly, the present invention is an on-machine-seamable laminated multiaxial press fabric for the press section of a paper machine. The press fabric comprises a first base fabric and a second base fabric.

The first base fabric is a multiaxial base fabric having a first fabric ply and a second fabric ply fashioned from an endless base fabric layer. The endless base fabric layer comprises a fabric strip having a first lateral edge, a second lateral edge, a plurality of lengthwise yarns and a plurality of crosswise yarns. The fabric strip is spirally wound in a plurality of contiguous turns wherein the first lateral edge in a given turn of the fabric strip abuts the second lateral edge of an adjacent turn thereof, thereby forming a helically continuous seam separating adjacent turns of the fabric strip. The helically continuous seam is closed by attaching abutting first and second lateral edges of the fabric strip to one another, thereby providing the base fabric layer in the form of an endless loop having a machine direction, a cross-machine direction, an inner surface and an outer surface.

The endless base fabric layer is flattened to produce the first fabric ply and the second fabric ply having two widthwise edges. The first fabric ply and the second fabric ply are connected to one another at folds along the two widthwise edges. At least one crosswise yarn in each of the turns of the fabric strip are removed at each of the folds at the two widthwise edges to provide unbound sections of lengthwise yarns of said fabric strip at the folds, the unbound sections being seaming loops for joining the widthwise edges of the flattened base fabric layer to one another to form an endless loop.

The second base fabric is an on-machine-seamable base fabric of substantially the same length as the first base fabric and has a plurality of seaming loops along its two widthwise edges. The second base fabric may be one produced by a modified endless weaving technique. Alternatively, it may be a multiaxial base fabric like the first base fabric.

In either case, at least one layer of staple fiber batt material is needled into one of the first and second fabric plies of the first base fabric and through the second base fabric to laminate the first and second base fabrics to one another.

5 The seaming loops of the first base fabric and the seaming loops of the second base fabric join the first and second base fabrics into endless form in one of the following two manners.

Firstly, the seaming loops at opposite ends of the first base fabric and the seaming loops at opposite ends of the second base fabric interdigitate with one another to define a single passage through which a pintle is directed to join the press
10 fabric into endless form.

Alternatively, the seaming loops at opposite ends of said first base fabric interdigitate with one another to define a first passage through which a first pintle is directed to form a first seam, and the seaming loop at opposite ends of the second base fabric interdigitate with one another to define a second passage through which a
15 second pintle is directed to form a second seam. The first seam is on the opposite side of the second seam relative to the first base fabric.

The present invention will now be described in more complete detail with frequent reference being made to the figures identified below.

20 BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a schematic top plan view illustrating a method for manufacturing the base fabric layer of the on-machine-seamable multiaxial press fabric of the present invention;

Figure 2 is a top plan view of the finished base
25 fabric layer;

Figure 3 is a cross-sectional view taken as indicated by line 3-3 in Figure 1;

Figure 4 is a top plan view of the base fabric layer in a flattened condition;

Figure 5 is a perspective view of the base fabric layer as shown in Figure 4;

Figure 6 is a schematic cross-sectional view of the flattened base fabric layer
30 taken as indicated by line 6-6 in Figure 4;

Figure 7 is a plan view of a portion of the surface of the base fabric layer;

Figure 8 is a plan view of the portion of the surface of the base fabric layer shown in Figure 7 following the removal of some of its crosswise yarns;

Figure 9 is a schematic cross-sectional view, analogous to that provided in Figure 6, following the removal of crosswise yarns;

5 Figure 10 is a schematic cross-sectional view of the press fabric of Figure 9 which has been flattened to form a two-ply fabric, with the unbound warp yarns forming seaming loops for on-machine seaming of the fabric;

Figure 11 is a cross-sectional view of an end portion of an on-machine-seamable base fabric;

10 Figure 12 is a cross-sectional view of the seam region of a laminated multiaxial press fabric of the present invention;

Figure 13 is a cross-sectional view of the seam region of a laminated multiaxial press fabric closed into endless form according to the prior art;

15 Figure 14 is a cross-sectional view of the seam region of a precursor of an embodiment of the laminated multiaxial press fabric of the present invention;

Figure 15 is a cross-sectional view of the seam region of the laminated multiaxial press fabric of the present invention closed into endless form in accordance with one embodiment thereof; and

20 Figure 16 is a cross-sectional view of the seam region of the laminated multiaxial press fabric of the present invention closed into endless form in accordance with an alternate embodiment thereof.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

Referring now to these figures, Figure 1 is a schematic top plan view
25 illustrating a method for manufacturing the base fabric layer of the on-machine-seamable multiaxial press fabric of the present invention. The method may be practiced using an apparatus 10 comprising a first roll 12 and a second roll 14, which are parallel to one another and which may be rotated in the directions indicated by the arrows. A woven fabric strip 16 is wound from a stock roll 18
30 around the first roll 12 and the second roll 14 in a continuous spiral. It will be recognized that it may be necessary to translate the stock roll 18 at a suitable rate

along second roll 14 (to the right in Figure 1) as the fabric strip 16 is being wound around the rolls 12, 14.

The first roll 12 and the second roll 14 are separated by a distance D, which is determined with reference to the total length required for the base fabric layer
5 being manufactured, the total length being measured longitudinally (in the machine direction) about the endless-loop form of the layer, it being understood that the total length is essentially twice the length of the on-machine-seamable multiaxial press fabric being manufactured. Woven fabric strip 16, having a width w, is spirally wound onto the first and second rolls 12,14 in a plurality of turns from stock roll 18,
10 which may be translated along the second roll 14 in the course of the winding. Successive turns of the fabric strip 16 are abutted against one another and are attached to one another along helically continuous seam 20 by sewing, stitching, melting, welding or gluing to produce base fabric layer 22 as shown in Figure 2. When a sufficient number of turns of the fabric strip 16 have been made to produce
15 layer 22 in the desired width W, that width being measured transversely (in the cross-machine direction) across the endless-loop form of the layer 22, the spiral winding is concluded. The base fabric layer 22 so obtained has an inner surface, an outer surface, a machine direction and a cross-machine direction. Initially, the lateral edges of the base fabric layer 22, it will be apparent, will not be parallel to the
20 machine direction thereof, and must be trimmed along lines 24 to provide the layer 22 with the desired width W, and with two lateral edges parallel to the machine direction of its endless-loop form.

Fabric strip 16 may be woven from monofilament, plied monofilament or multifilament yarns of a synthetic polymeric resin, such as polyester or polyamide,
25 in the same manner as other fabrics used in the papermaking industry are woven. After weaving, it may be heat-set in a conventional manner prior to interim storage on stock roll 18. Fabric strip 16 includes lengthwise yarns and crosswise yarns, wherein, for example, the lengthwise yarns may be plied monofilament yarns while the crosswise yarns may be monofilament yarns. Further, fabric strip 16 may be of a
30 single- or multi-layer weave.

Alternatively, fabric strip 16 may be woven and heat-set in a conventional manner, and fed directly to apparatus 10 from a heat-set unit without interim storage

on a stock roll 18. It may also be possible to eliminate heat-setting with the proper material selection and product construction (weave, yarn sizes and counts).

Figure 3 is a cross section of fabric strip 16 taken as indicated by line 3-3 in Figure 1. It comprises lengthwise yarns 26 and crosswise yarns 28, both of which are represented as monofilaments, interwoven in a single-layer weave. More specifically, a plain weave is shown, although, it should be understood, the fabric strip 16 may be woven according to any of the weave patterns commonly used to weave paper machine clothing. Because the fabric strip 16 is spirally wound to assemble base fabric layer 22, lengthwise yarns 26 and crosswise yarns 28 do not align with the machine and cross-machine directions, respectively, of the layer 22. Rather, the lengthwise yarns 26 make a slight angle, θ , whose magnitude is a measure of the pitch of the spiral windings of the fabric strip 16, with respect to the machine direction of the layer 22, as suggested by the top plan view thereof shown in Figure 2. This angle, as previously noted, is typically less than 10° . Because the crosswise yarns 28 of the fabric strip 16 generally cross the lengthwise yarns 26 at a 90° angle, the crosswise yarns 28 make the same slight angle, θ , with respect to the cross-machine direction of the layer 22.

Woven fabric strip 16 has a first lateral edge 30 and a second lateral edge 32 which together define the width of the body of the woven fabric strip 16. As the fabric strip 16 is being spirally wound onto the first and second rolls 12, 14, the first lateral edge 30 of each turn is abutted against the second lateral edge 32 of the immediately preceding turn.

Once the base fabric layer 22 has been assembled, it may be heat-set prior to being removed from apparatus 10. After removal, it is flattened as shown in the plan view presented in Figure 4. This places base fabric layer 22 into the form of a two-ply fabric of length L, which is equal to one half of the total length of the base fabric layer 22 as manufactured on apparatus 10, and width W. Seam 20 between adjacent turns of woven fabric strip 16 slants in one direction in the topmost of the two plies, and in the opposite direction in the bottom ply, as suggested by the dashed lines in Figure 4. Flattened base fabric layer 22 has two widthwise edges 36.

Figure 5 is a perspective view of the base fabric layer 22 in a flattened condition. At the two widthwise edges 36 of the flattened base fabric layer 22 are folds 38, which align with the transverse, or crossmachine, direction thereof.

Figure 6 is a schematic cross-sectional view taken as indicated by line 6-6 in Figure 4. In accordance with the present invention, a plurality of crosswise yarns 28 of fabric strip 16 and of segments thereof are removed from adjacent the folds 38 to produce a first fabric ply 40 and a second fabric ply 42 joined to one another at their widthwise edges 36 by unbound sections of lengthwise yarns 26.

The provision of the unbound sections of lengthwise yarns 26 at the two widthwise edges 36 of the flattened base fabric layer 22 is complicated by two factors. Firstly, because the fabric strip 16 has a smaller width than the base fabric layer 22, its crosswise yarns 28 do not extend for the full width of the base fabric layer 22. Secondly, and more importantly, because the fabric strip 16 is spirally wound to produce base fabric layer 22, its crosswise yarns do not lie in the cross-machine direction of the base fabric layer 22 and therefore are not parallel to the folds 38. Instead, as discussed above, the crosswise yarns 28 make a slight angle, θ , typically less than 10° , with respect to the cross-machine direction of the base fabric layer 22. Accordingly, in order to provide the unbound sections of lengthwise yarns 26 at folds 38, crosswise yarns 28 must be removed in a stepwise fashion from the folds 38 across the width W, of the base fabric layer 22.

For purposes of illustration, Figure 7 is a plan view of a portion of the surface of base fabric layer 22 at a point on one of the folds 38 near the spirally continuous seam 20 between two adjacent spiral turns of fabric strip 16. Lengthwise yarns 26 and crosswise yarns 28 are at slight angles with respect to the machine direction (MD) and cross-machine direction (CD), respectively.

The fold 38, which is flattened during the removal of the neighboring crosswise yarns 28, is represented by a dashed line in Figure 7. In practice, the base fabric layer 22 would be flattened, as described above, and the folds 38 at its two widthwise edges 36 marked in some manner, so that its location would be clear when it was flattened. In order to provide the required unbound sections of lengthwise yarns 26 at the fold 38, it is necessary to remove the crosswise yarns 28 from a region, defined by dashed lines 46,48 equally separated from fold 38 on

opposite sides thereof. Because crosswise yarns 28 are not parallel to fold 38 or dashed lines 46,48, it is often necessary to remove only a portion of a given crosswise yarn 28, such as in the case with crosswise yarn 50 in Figure 7, in order to clear the space between dashed lines 46,48 of crosswise yarns 28.

5 Figure 8 is a plan view of the same portion of the surface of base fabric layer 22 as is shown in Figure 7 following the removal of the crosswise yarns 28 from the region centered about the fold 38. Unbound sections 44 of lengthwise yarns 26 extend between dashed lines 46,48 in the region of the fold 38. The portion of crosswise yarn 50 which extended past dashed line 46 has been removed, as noted
10 above.

 Following the removal of the crosswise yarns 28 from the region centered about the fold 38, the base fabric layer 22 is again flattened so that first fabric ply 40 and second fabric ply 42 are joined to one another by unbound sections 44 of lengthwise yarns 26. Figure 9 is a schematic cross-sectional view, analogous to that
15 provided in Figure 6, of one of the two widthwise edges 36 of the flattened base fabric layer 22.

 Referring to Figure 10, a loop-forming cable 52 is next installed between first fabric ply 40 and second fabric ply 42 and against unbound sections 44 of lengthwise yarns 26. Stitches 54, for example, may be made to connect first fabric
20 ply 40 to second fabric ply 42 adjacent to loop forming cable 52 to form seaming loops 56 from the unbound sections 44 of the lengthwise yarns 26. Alternatively, first fabric ply 40 may be connected to second fabric ply 42 adjacent to loop-forming cable 52 by any of the other means used for such a purpose by those of ordinary skill in the art.

25 Figure 11 is a cross-sectional view of an end portion of an on-machine-seamable base fabric 60. Base fabric 60 comprises lengthwise yarns 64, which form seaming loops 66 along each of its two widthwise edges, and crosswise yarns 62 (shown in cross-section). Base fabric 60 has a length and width substantially equal to that of base fabric layer 22.

30 On-machine-seamable base fabric 60 may be produced by a modified endless weaving technique wherein weft yarns, which are ultimately the lengthwise yarns 64, are continuously woven back and forth across the loom, at the end of each

passage thereacross forming a seaming loop 66 on one of the two widthwise edges of the fabric being woven by passing around a loop-forming pin. During the modified endless weaving process, the crosswise yarns 62 of the on-machine-seamable base fabric 60 are warp yarns. Several schemes, disclosed and claimed in
5 U.S. Patent No. 3,815,645 to Codorniu, the teachings of which are incorporated herein by reference, for weaving on-machine-seamable base fabric 60 by modified endless weaving are available and may be used in the practice of the present invention.

The fabric being woven to provide on-machine-seamable base fabric 60 may
10 be either single- or multi-layer, and may be woven from monofilament, plied monofilament or multifilament yarns of a synthetic polymeric resin, such as polyester or polyamide. The weft yarns, which form the seaming loops 66 and are ultimately the lengthwise yarns 64, are preferably monofilament yarns.

Figure 12 is a cross-sectional view of the seam region of a laminated fabric
15 comprising an on-machine-seamable base fabric layer 22 and an on-machine-seamable base fabric 60. Alternatively, a second on-machine-seamable base fabric layer 22 may be used instead of on-machine-seamable base fabric 60. In any event, on-machine-seamable base fabric layer 22 and on-machine-seamable base fabric 60, or an on-machine-seamable alternative therefor, are joined to one another by one or
20 more layers of staple fiber batt material 80 needled into and through the superimposed base fabric layer 22 and base fabric 60 to complete the manufacture of the present on-machine-seamable laminated multiaxial press fabric. The staple fiber batt material 80 is of a polymeric resin material, and preferably is of a polyamide or polyester resin.

Referring to Figure 13, a cross-sectional view of the seam region of a
25 laminated fabric of the prior art, the seaming loops 56 of base fabric layer 22 are interdigitated together, and a seam 70 formed by the insertion of pintle 58, and the seaming loops 66 of base layer 60 are interdigitated together and seam 72 formed by the insertion of pintle 68. The resulting structure is a laminated press fabric,
30 comprising base fabric layer 22 and base fabric 60, having two seams 70,72 with seam 70 being vertically stacked relative to seam 72.

Figure 14 is a cross-sectional view of the seam region of a precursor of one of the embodiments of the laminated multiaxial press fabric of the present invention. The press fabric comprises base fabric layer 22 having seaming loops 56 and fabric 60 having seaming loops 66. Without removing loop-forming cables 52 from base fabric layer 22, as shown in Figure 10, seaming loops 66 of base fabric 60 are inserted between seaming loops 56 of base fabric layer 22. Then the seaming loops 66 of base fabric 60 are interdigitated and connected with pintle 68 to form seam 72. The seaming loops 56 of base fabric layer 22 are thereby secured on the opposite side of base fabric 60 from base fabric layer 22.

Figure 15 is a cross-sectional view of the seam region of the laminated multiaxial press fabric of the present invention following the removal of loop-forming cables 52 shown in Figure 14 and the interdigitation and joining of seaming loops 56 with pintle 58. The seaming loops 56 of base fabric layer 22 are connected with pintle 58 on the opposite side of base fabric 60 from base fabric layer 22 to form seam 70. In other words, the positions of the seams 70,72 are reversed relative to those shown in Figure 13, although seams 70,72 remain vertically stacked relative to one another. It should be noted that the seaming loops at opposite ends of the fabric may be at different lengths. While they will be long enough to extend through the seam area and seam thickness of the other base fabric layer, a set of longer loops on one end will result in a seam offset from the other seam. In certain applications this may be desirable.

Figure 16 is a cross-sectional view of the seam region of an alternate embodiment of the laminated multiaxial press fabric of the present invention. Seaming loops 56 of base fabric layer 22 and seaming loops 66 of base fabric 60 are joined together with a common pintle 74 to form a single seam 76.

Modifications to the above would be obvious to one of ordinary skill in the art, but would not bring the invention so modified beyond the scope of the appended claims.

WHAT IS CLAIMED IS:

1. An on-machine-seamable laminated multiaxial press fabric for the press section of a paper machine, said press fabric comprising:

a first base fabric, said first base fabric having a first fabric ply and a second fabric ply fashioned from an endless base fabric layer, said endless base fabric layer comprising a fabric strip having a first lateral edge, a second lateral edge, a plurality of lengthwise yarns and a plurality of crosswise yarns, said fabric strip being spirally wound in a plurality of contiguous turns wherein said first lateral edge in a given turn of said fabric strip abuts said second lateral edge of an adjacent turn thereof, thereby forming a helically continuous seam separating adjacent turns of said fabric strip, said helically continuous seam being closed by attaching abutting first and second lateral edges of said fabric strip to one another, thereby providing said base fabric layer in the form of an endless loop having a machine direction, a cross-machine direction, an inner surface and an outer surface, said endless base fabric layer being flattened to produce said first fabric ply and said second fabric ply having two widthwise edges, said first fabric ply and said second fabric ply being connected to one another at folds along said two widthwise edges, at least one crosswise yarn in each of said turns of said fabric strip being removed at each of said folds at said two widthwise edges to provide unbound sections of lengthwise yarns of said fabric strip at said folds, said unbound sections being seaming loops for joining said widthwise edges of said flattened base fabric layer to one another to form an endless loop;

a second base fabric, said second base fabric being an on-machine-seamable base fabric of substantially the same length as said first base fabric and having a plurality of seaming loops along its two widthwise edges; and

at least one layer of staple fiber batt material needled into one of said first and second fabric plies of said first base fabric and through said second base fabric to laminate said first and second base fabrics to one another,

wherein said seaming loops of said first base fabric and said seaming loops of said second base fabric join said first and second base fabrics into endless form in one of the following two manners:

a) said seaming loops at opposite ends of said first base fabric and said seaming loops at opposite ends of said second base fabric interdigitate with one another to define a single passage through which a pintle is directed to join said press fabric into endless form; or

5 b) said seaming loops at opposite ends of said first base fabric interdigitate with one another to define a first passage through which a first pintle is directed to form a first seam, and said seaming loops at opposite ends of said second base fabric interdigitate with one another to define a second passage through which a second pintle is directed to form a second seam, said first seam being on an opposite
10 side of said second seam relative to said first base fabric.

2. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 1 wherein said second base fabric is an on-machine-seamable base fabric comprising lengthwise and crosswise yarns, said lengthwise yarns forming seaming
15 loops along two widthwise edges of said second base fabric.

3. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 1 wherein said second base fabric has a first fabric ply and a second fabric ply fashioned from an endless base fabric layer, said endless base fabric layer
20 comprising a fabric strip having a first lateral edge, a second lateral edge, a plurality of lengthwise yarns and a plurality of crosswise yarns, said fabric strip being spirally wound in a plurality of contiguous turns wherein said first lateral edge in a given turn of said fabric strip abuts said second lateral edge of an adjacent turn thereof, thereby forming a helically continuous seam separating adjacent turns of said fabric
25 strip, said helically continuous seam being closed by attaching abutting first and second lateral edges of said fabric strip to one another, thereby providing said base fabric layer in the form of an endless loop having a machine direction, a cross-machine direction, an inner surface and an outer surface, said endless base fabric layer being flattened to produce said first fabric ply and said second fabric ply
30 having two widthwise edges, said first fabric ply and said second fabric ply being connected to one another at folds along said two widthwise edges, at least one crosswise yarn in each of said turns of said fabric strip being removed at each of said

folds at said two widthwise edges to provide unbound sections of lengthwise yarns of said fabric strip at said folds, said unbound sections being seaming loops for joining said widthwise edges of said flattened base fabric layer to one another to form an endless loop.

5

4. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 1 wherein said fabric strip is woven from said lengthwise and crosswise yarns.

5. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 1 wherein said fabric strip is of a single-layer weave.

10

6. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 1 wherein said fabric is of a multi-layer weave.

7. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 1 wherein said lengthwise yarns and said crosswise yarns of said fabric strip are of a synthetic polymeric resin.

15

8. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 1 wherein said first base fabric has lateral edges trimmed in a direction parallel to said machine direction thereof.

20

9. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 1 wherein said fabric strip makes an angle of less than 10° with respect to said machine direction of said first base fabric.

25

10. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 2 wherein said second base fabric is woven from said lengthwise and crosswise yarns.

30

11. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 2 wherein said second base fabric is of a single-layer weave.

12. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 2 wherein said second base fabric is of a multi-layer weave.
- 5 13. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 2 wherein said lengthwise yarns and said crosswise yarns of said second base fabric are of a synthetic polymeric resin.
- 10 14. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 2 wherein said lengthwise yarns of said second base fabric are monofilament yarns.
- 15 15. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 3 wherein said fabric strip of said second base fabric is woven from said lengthwise and crosswise yarns.
16. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 3 wherein said fabric strip of said second base fabric is a single-layer weave.
- 20 17. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 3 wherein said fabric strip of said second base fabric is of a multi-layer weave.
18. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 3 wherein said lengthwise yarns and said crosswise yarns of said fabric strip
25 of said second base fabric are of a synthetic polymeric resin.
19. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 3 wherein said second base fabric has lateral edges trimmed in a direction parallel to said machine direction thereof.

30

20. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 3 wherein said fabric strip of said second base fabric makes an angle of less than 10° with respect to said machine direction of said second base fabric layer.
- 5 21. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 1 wherein said staple fiber batt material is of a polymeric resin material.
22. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 21 wherein said polymeric resin material is selected from the group consisting
10 of polyamide and polyester resins.
23. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 1 further comprising at least one layer of staple fiber batt material needled into said second base fabric and through one of said first and second fabric plies of said
15 first base fabric.
24. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 23 wherein said staple fiber batt material is of a polymeric resin material.
- 20 25. An on-machine-seamable laminated multiaxial press fabric as claimed in claim 24 wherein said polymeric resin material is selected from the group consisting of polyamide and polyester resins.




FIG. 1





FIG. 2

FIG. 3



4/12




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11

10/12




FIG. 12







FIG. 13
(PRIOR ART)

11/12

*FIG. 14**FIG. 15*

12/12

*FIG. 16*

INTERNATIONAL SEARCH REPORT

Internat Application No

PCT/us 03/07534

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 D21F7/08 D21F7/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D21F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 984 100 A (ALBANY INT CORP) 8 March 2000 (2000-03-08) the whole document ---	1-5, 7-9, 11-16, 18-25
A	US 4 940 630 A (PENVEN PATRICK H) 10 July 1990 (1990-07-10) -----	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

° Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

6 August 2003

Date of mailing of the international search report

20/08/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Gast, D

INTERNATIONAL SEARCH REPORT

Internationa Application No
PCT/US 03/07534

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0984100	A	08-03-2000	US 6117274 A	12-09-2000
			AU 713832 B1	09-12-1999
			BR 9805466 A	06-06-2000
			CN 1246410 A	08-03-2000
			EP 0984100 A2	08-03-2000
			JP 2000080584 A	21-03-2000
			KR 2000022001 A	25-04-2000
			NO 984579 A	06-03-2000
			NZ 332189 A	26-05-2000
			TW 483959 B	21-04-2002
			ZA 9809829 A	04-05-1999

US 4940630	A	10-07-1990	US 4824525 A	25-04-1989
			CA 1318165 C	25-05-1993
			US 4892781 A	09-01-1990
